

11-16-00

A

Modified PTO 1082

Case Docket No IGB 1532

BOX PATENT APPLICATION  
 ASSISTANT COMMISSIONER FOR PATENTS  
 Washington, D.C. 20231

Sir:

Transmitted herewith for filing is the patent application of:

Inventor(s): **Jeffrey Ronald KING; Karen TAYLOR; Simon Richard John LEE; Stefan SCHUTTEL; and Roger Leslie BRETNALL**

For: **PRINTING PROCESS**

Enclosed are:

- ☒ Specification and claims.  
☒ Inventors' Declaration and Power of Attorney (TWO SEPARATE).  
 \_\_\_\_\_ sheet of (informal) drawings.  
☒ Certified copy of priority Great Britain appln. 9927167.8

The filing fee has been calculated as follows:

	(Col.1)	(Col.2)	LARGE ENTITY
FOR:	NO. FILED	NO. EXTRA	RATE FEE
BASIC FEE			\$ 710
TOTAL CLAIMS	24-20	4	x 18 72
INDEP CLAIMS	2- 3		x 80
MULTIPLE DEPENDENT CLAIMS			x 270 --

\* If the difference in Col.1 is less than zero, enter "0" in Col.2

Fee for recordation of Assignment

40

TOTAL \$ 822

- Our check in the amount of \$ \_\_\_\_\_ is enclosed for the filing (and assignment recordation) fee(s).  
☒ Please charge Deposit Account No. 50-1541 in the amount of \$ 822.  
 Triplicate copies of this sheet are enclosed.  
☒ The Commissioner is hereby authorized to charge any under-payment of fees required for the filing of this application, or credit any overpayment, to Deposit Account No. 50-1541. Triplicate copies of this sheet are enclosed.  
 The Commissioner is hereby authorized to charge any under-payment of fees required to maintain the pendency of this application, or to credit any overpayment, to Deposit Account No. 50-1541. Triplicate copies of this sheet are enclosed.

**X CERTIFICATE OF EXPRESS MAILING:**

I hereby certify that the aforementioned papers are being deposited with the United States Postal Service on the date shown below in an envelope addressed to:

BOX PATENT APPLICATION  
 ASSISTANT COMMISSIONER FOR PATENTS  
 Washington, D.C. 20231

Certificate Number EL70642067145  
 Date: November 15, 2000

Respectfully submitted,



Dara L. Onofrio  
 Attorney for Applicant(s)  
 Registration No. 34,889

JC564 U.S. PAT. & T.M. OFFICE  
 09/13/00  
 11/15/00

09/13/00 11/15/00

11/15/00  
 JC562 U.S. PAT. & T.M. OFFICE

## PRINTING PROCESS

### FIELD OF INVENTION

This invention relates to a recording medium and to a method for  
5 the treatment of images produced therewith.

### BACKGROUND OF THE INVENTION

This invention relates to a recording medium particularly suitable to  
use with ink jet printers and to a method for the treatment of images  
10 prepared therewith. It particularly relates to images produced using so-  
called aqueous inks, that is to say inks in which water comprises the  
major component of the liquid phase. There is increasing interest in the  
use of aqueous inks for environmental and safety reasons.

Printing media suitable for use with ink jet printers are well known.  
15 Commonly these employ at least one ink receiving layer coated on a  
suitable substrate. The purpose of the receiving layer is to take up the  
ink rapidly and improve image quality. One problem with images  
produced using aqueous inks is that they can be insufficiently robust to  
handling, and that the image or the receiving layer on which it is printed  
20 is sensitive to rubbing and scratching. In addition the printed image  
frequently becomes more sensitive to handling and damage under  
damp conditions, and can sometimes be washed completely away.

Several methods of overcoming the poor robustness of images  
produced using aqueous inks are known. For instance various  
25 additional coatings and treatments for ink receiving layers have been  
proposed, such as lacquers or varnishes which have to be applied  
after printing the image, thus requiring additional equipment. For  
instance our British Patent Application 2337482 A provides a method  
for increasing the rub resistance of an image by coating or over-  
30 printing the image with an aqueous solution of a styrene acrylate  
polymer.

Another method of improving the robustness of printed images is to  
lamine or encapsulate them, and this is particularly common when

they are intended for external display. By lamination is meant the combination of a printed image with a transparent overlay, this combination usually being accomplished with an adhesive activated by heat, pressure, or both. The overlay acts as a physical protection for the image and completely seals it from ingress of water. By encapsulation is meant the combination of a printed image layer between two laminating sheets, that on the image surface being transparent, the combination being accomplished with an adhesive activated by heat, pressure, or both. Encapsulation is most effective if the laminating sheets extend beyond the printed image and are bonded to each other at the extremities, thus preventing ingress of water through exposed edges of the image.

However lamination and encapsulation are both expensive because additional materials are required together with additional handling and equipment, and there is considerable interest in finding a cheaper and simpler method of increasing the robustness of images produced using aqueous inks.

As an alternative to lamination or overprinting, Japanese Patent Applications 59/222381, 07/237348, 08/02090, and 09/104164 and European Patent Applications 0 858 905 and 0 858 906 disclose a heat seal method of protecting an ink jet image wherein the receiving system comprises two layers coated on a suitable base. The lower layer is an ink receiving layer which is absorbent to the ink, whereas the upper layer comprises a film forming polymer in a binder. After printing the upper layer may be sealed by heating to form a robust barrier to protect the image in the lower layer. This is similar to laminating the image, but does not require the additional expensive lamination sheet.

However this heat seal method needs to achieve high temperatures to seal the image (up to 170°C being given in the Examples of EP 0 858 906 A) and also requires a relatively complicated and expensive receiving sheet. There is thus still a need for an imaging material and method which will provide images resistant to washing and handling

when printed using aqueous inks without lamination. We have found a material and method which achieves these objectives.

## 5     SUMMARY OF THE INVENTION

According to the present invention there is provided a printing method which comprises the steps of:-

1) Printing on to a receiving material which comprises on a suitable substrate at least one ink receiving layer which comprises a particulate  
10 polymer which is characterised by a film forming temperature of between 60° to 140°C together with at least one binder, and

2) Subsequently heating and applying pressure to the printed image to fuse the polymer.

The method and materials of the invention are much simpler than  
15 previously known heat sealing methods for printed images because the receiving layer may consist of only a single layer rather than the minimum of two known previously, and is thus considerably simpler and cheaper to manufacture. The receiving layers of the invention provide bright images after printing and fusing which show a high level  
20 of scratch and rub resistance even when wet.

## DETAILED DESCRIPTION OF THE INVENTION

Suitable substrates to carry the layers of the invention include any  
25 of those commonly used for printing and imaging media, for example paper, high wet-strength paper, tracing paper, heavyweight paper, card, board, treated paper such as resin or polyethylene coated paper, transparency materials, synthetic papers, canvas, cloth, fabric, metals such as aluminium, and polymeric substrates such as cellulose  
30 acetates, poly(ethylene), poly(propylene), poly (vinyl chloride), and polyesters including poly (ethylene terephthalate) and poly (ethylene naphthalate).

Preferably the binder is a hydrophilic binder. Suitable hydrophilic binders include poly (vinyl alcohol), copolymers of poly (vinyl alcohol), carbohydrates such as tragacanth gum or starch, modified carbohydrates such as hydroxyethyl cellulose or carboxymethyl cellulose, polyacrylates, poly (vinyl pyrrolidone), poly(ethylene imine), gelatin, casein and mixtures of such binders. A particularly suitable hydrophilic binder is poly (vinyl alcohol). It is to be understood that commercial samples of poly (vinyl alcohol) are normally prepared by hydrolysis of poly (vinyl acetate), and that this hydrolysis does not always go to completion. Thus a preferred hydrophilic binder is poly (vinyl alcohol) which has a degree of hydrolysis of at least 90%, and a particularly preferred binder is poly (vinyl alcohol) which has a degree of hydrolysis of about 99%. This is hereinafter referred to as 99%PVA.

Suitable polymers for the particulate polymer include low density polyethylene and copolymers of ethylene with other ethylenically unsaturated monomers, such as acrylate monomers. A suitable particle size for the particulate polymer is between about 1  $\mu\text{m}$  and about 50  $\mu\text{m}$ , with a particle size between about 5  $\mu\text{m}$  and about 20  $\mu\text{m}$  being preferable. A particularly suitable particulate polymer comprises low density polyethylene spherical beads having an average diameter of about 12  $\mu\text{m}$ . Another particularly suitable particulate polymer comprises spherical beads of a 7% acrylic acid/ polyethylene copolymer having an average diameter of about 10  $\mu\text{m}$ . Another suitable particulate polymer comprises polyethylene beads of random shape and a particle size of about 25  $\mu\text{m}$ . These polymers have crystalline melting points of 105-107°C.

A suitable coating weight for the receiving layer is from about 5 to about 50  $\text{gm}^{-2}$ . A preferred coating weight for the receiving layer is from about 20 to about 40  $\text{gm}^{-2}$ . The ratio of the coating weight of the particulate polymer to that of the hydrophilic binder may be from about 20:1 to about 1:1, but preferably is between about 10:1 and about 5:1.

0057057266

The receiving layer may advantageously also comprise additives which are commonly added to ink receiving layers such as surfactants to improve coating quality, cross linking agents, optical brightening agents, inorganic pigments or fillers such as chalk, silica, alumina, kaolin and the like, light stabilisers, biocides, and dye fixatives such as the polymers provided by United States Patents 5,342,688, 5,589,269, and 5,712,027. Suitable cross linking agents for the preferred poly (vinyl alcohol) binders of the invention include aldehydes such as glyoxal, boric acid, poly ethylene imines, and divalent metallic cations.

According to a preferred aspect of this invention, the printed image is heated by passing through a laminator. By laminator is meant a device which is normally used for the lamination of printed images which comprises a means of heating and pressing together the image and the laminating sheet thus causing the two to adhere, commonly by passing them through a nip between a pair of heated rollers. This aspect is particularly preferable because many printing and processing houses already possess and use laminators which can be applied to the materials of this invention. However the advantage of this invention is that the additional expensive lamination sheet is unnecessary.

According to another aspect of the invention, the printed image is heated by passing through a laminator in conjunction with a second, inert sheet which is held against the image protective layer of the material. The inert sheet does not adhere to the material, but protects it from the rollers of the laminator. Moreover the use of a smooth inert sheet will impart a high gloss or other desired appearance to the final image. Alternatively a suitable choice of the inert sheet may be used to produce a pattern such as a security symbol after contacting with the image. The inert sheet may then be recycled almost indefinitely.

The method and materials of the invention are particularly suited to the treatment of images produced using ink jet printers. Aqueous inks are commonly used in such printers, particularly those designed for use in the home or office, but the invention is also suitable for ink jet printers using non-aqueous inks such as those based on mineral oils

and organic solvents. Ink jet printing is a non impact printing method that in response to a digital signal produces droplets of ink that are deposited on a substrate to produce an image. Ink jet printing has found broad application in recent years. Any convenient ink jet printer  
5 may be used, for example a continuous printer or a piezoelectric or thermal drop-on-demand printer.

The invention may also be used with other printing methods such as flexographic printing, with pen type plotters, or with marker pens and the like. Suitable colorants for the inks include dyes or pigments.

10 Preferred inks for the invention are pigmented aqueous inks.

The materials and method of this invention are suitable for many uses where robustness of an ink jet image is important, such as posters, banners, displays, labels, and the like. The method of this invention is also particularly suitable for use with a wide variety of  
15 packaging materials, e.g a heavy weight paper, card, or board.

The materials and method of this invention are also particularly suitable as a security printing system, and this aspect of the invention is especially preferred. After the material has been sealed by heating it is no longer receptive to inks, and is thus difficult to alter and offers  
20 high levels of protection from fraud and forgery. In an additional aspect of the invention when it is used as a security printing system, a suitable mark or pattern such as, for example, a holographic pattern may be embossed on or transferred to the image at the heating stage. This pattern may be carried on the inert sheet used in contact with the  
25 image during the heating stage, or may be carried on a roller or stamp used in contact with the image at the heating stage.

Various ink receiving materials which comprise a combination of a particulate polymer and a hydrophobic binder are already known. For instance United States Patent 3,968,319 discloses a particulate  
30 polymer for use in paper coatings, United States Patent 4,196,253 discloses a paper coated with a binder and organic particles, United states Patent 4,371,582 discloses an ink jet recording sheet containing a basic latex polymer, 4,442,247 discloses a coating composition

comprising a combination of an aqueous resin with an insoluble resin, United States Patent 4,686,118 discloses a recording medium wherein the coating comprises a combination of a hydrophilic and a hydrophobic polymer, United States Patent 5,102,731 discloses a recording medium wherein the coated layer comprises a hydrophilic urethane resin and fine organic or inorganic particles, United States Patent 5,254,403 discloses a coated recording sheet wherein the receiving layer comprises a mixture of a latex polymer with two hydrophilic polymeric binders, United States Patent 5,270,103 discloses a receiver sheet coated with a coating comprising a pigment, a binder, and a latex polymer, United States Patent 5,405,678 discloses a coating comprising a latex polymer which has not been completely coalesced, United States Patent 5,672,392 discloses a process for preparing ink jet recording materials whereof the coatings comprise starch, an insoluble copolymer, and a binder, United States Patent 5,714,235 discloses an ink jet recording sheet containing casein and a styrene-butadiene rubber, United States Patent 5,925,712 discloses a fusible printable coating wherein one of the alternative compositions comprises a combination of a powdered thermoplastic polymer and a binder, and Japanese Patent Applications 59/204591 and 59/204592 disclose ink jet receiving coatings which comprise microcapsules which are ruptured after printing to improve the robustness of the image. However the method of this invention is novel and the coatings are particularly suitable for the method.

The following Examples will serve to illustrate the invention:-

### EXAMPLE 1

A formulation was prepared using the following components:-

Poly (vinyl alcohol) 10% solution	40.0g
Silicone surfactant	0.2g
Ethylene acrylic acid copolymer beads	25.0g
Optical Brightening Agent	0.2g
Deionised water	34.6g



This formulation was coated on to a subbed poly (vinyl chloride) substrate to give a coating weight of  $25\text{gm}^{-2}$ . An image was printed with pigmented inks using a Novajet III printer, and the coating was passed through a GBC 1200 laminator at a heat setting corresponding to a temperature of  $120^{\circ}\text{C}$  together with a piece of paper to seal the image. The paper was removed leaving a smooth clear glossy image which was resistant to wet rubbing.

## EXAMPLE 2

A formulation was prepared using the following components:-

Poly (vinyl alcohol) 10% solution	400g
Silicone surfactant	2g
Polyethylene beads	250g
Deionised water	348g

The poly (vinyl alcohol) used was a commercial sample from Harco under the trade name Mowiol 28-99 having a degree of hydrolysis of 99%. The surfactant was from BYK Chemie under the trade name BYK 348. The polyethylene beads were low density polyethylene spherical beads having an average diameter of about  $12\text{ }\mu\text{m}$  available under the trade name Flothene from Sumitomo. The formulation was coated on to a substrate comprising plain paper having a substance of  $80\text{gm}^{-2}$  to give a wet coating weight of  $100\text{gm}^{-2}$ , approximately  $29.2\text{ gm}^{-2}$  when dry. An image was printed with pigmented inks using a Novajet III printer, and the coating was passed through a GBC 1200 laminator at a heat setting corresponding to a temperature of  $115^{\circ}\text{C}$  with the image surface in contact with a piece of clear film to seal the image. The film was removed leaving a smooth clear glossy image which was resistant to wet rubbing.

### EXAMPLE 3

A formulation was prepared using the following components:-

Poly (vinyl alcohol) 10% solution	400g
Silicone surfactant	2g
Polyethylene particles	250g
Deionised water	348g

5

The poly (vinyl alcohol) used was a commercial sample from Harco under the trade name Mowiol 56-98 having a degree of hydrolysis of 98%. The surfactant was from BYK Chemie under the trade name BYK 348. The polyethylene particles were low density polyethylene particles of random shape and average particle size about 25  $\mu\text{m}$  available under the trade name Coathylene HX1681 from duPont. The formulation was coated on to a substrate comprising plain paper having a substance of  $80\text{gm}^{-2}$  to give a wet coating weight of  $100\text{gm}^{-2}$ , approximately  $29.2\text{ gm}^{-2}$  when dry. An image was printed with pigmented inks using a Novajet III printer, and the coating was passed through a GBC 1200 laminator at a heat setting corresponding to a temperature of  $115^{\circ}\text{C}$  with the image surface in contact with a piece of clear film to seal the image. The film was removed leaving a smooth clear glossy image which was resistant to wet rubbing.

Finally, it is understood that variations and modifications from the examples given herein are possible in view of the foregoing disclosure. Therefore, although the invention has been described with reference to certain preferred embodiments it will be appreciated that other ink receiving layer materials may be used, which are nevertheless within the scope and spirit of the invention as defined in the claims appended hereto.

30

## CLAIMS :-

1. A recording medium for ink jet printing comprising:  
a substrate coated with at least one ink receiving layer comprising a  
5 particulate polymer having film forming temperatures between 60 to  
140 °C and a binder.
2. The recording medium according to claim 1, wherein said  
substrate is selected from the group consisting of paper,  
10 transparency materials, fabrics, canvas, cloth, transfer materials  
and polymeric substrates.
3. The recording medium according to claim 2, wherein said paper  
is selected from the group consisting of high wet-strength paper,  
15 tracing paper, heavy weight paper, cardboard, label grade  
paper, treated paper, pigmented paper, resin coated paper,  
polyethylene coated paper and synthetic paper.
4. The recording medium according to claim 2, wherein said  
20 polymeric substrate is selected from the group consisting of  
cellulose acetates, polyesters, poly(propylene) and poly(vinyl  
chloride).
5. The recording medium according to claim 1, wherein said ink  
25 receiving layer includes at least one binder selected from the  
group consisting of gelatin, poly(vinyl alcohol), poly(vinyl

pyrrolidone), carbohydrates, gums, treated carbohydrates, hydroxyethyl cellulose, carboxymethyl cellulose, acrylic polymers, casein, starch and mixtures thereof.

- 5        6. The recording medium according to claim 5, wherein said ink receiving layer comprises poly (vinyl alcohol) having a degree of hydrolysis of at least 90%.
- 10       7. The recording medium according to claim 5, wherein said ink receiving layer further includes one or more additives selected from the group consisting of inorganic pigments, fillers, silica, alumina, clays, calcium carbonate, dye fixing agents, cationic polymers, surfactants, cross linking agents, optical brighteners and light stabilizers.
- 15       8. The recording medium according to claim 1, wherein said particulate polymer has a particle size between 1 and 50 $\mu$ m.
- 20       9. The recording medium according to claim 1, wherein said particulate polymer is selected from the group consisting of low density polyethylene and copolymers of ethylene with ethylenically unsaturated monomers.
- 25       10. The recording medium according to claim 9, wherein said ethylenically unsaturated monomers comprise acrylic acid.

11. The recording medium according to claim 1, wherein said particulate polymer comprises low density polyethylene particles having an average particle size of approximately 25 $\mu$ m.

5

12. The recording medium according to claim 1, wherein said ink receiving layer has a coating weight from 5 to 50 gm<sup>-2</sup>.

13. An ink jet printing method comprising the steps of:

- 10           a. printing on to a receiving medium which comprises a substrate coated with at least one ink receiving layer comprising polymeric particles having film forming temperatures between 60 to 140 °C and a binder; and
- 15           b. heating the printed image to form a stable image-protecting coating.

14. A method according to claim 13, wherein said ink receiving layer is coated as an aqueous formulation on top of said substrate.

20           15. A method according to claim 13, wherein the printed image is heated under pressure to form the protective coating.

16. A method according to claim 13, wherein the printed image is heated by passing through a laminator.

17. A method according to claim 16, wherein an inert sheet is in contact with said ink receiving layer and passed through said laminator.

5 18. A method according to claim 17, wherein said inert sheet is selected from the group consisting of release papers, release liners, silicone release liners, casting films, casting papers and polyester films.

10 19. A method according to claim 17, wherein said inert sheet is used to impart a high gloss, embossed pattern or security symbol to the final image.

15 20. A method according to claim 13, wherein said binder is a hydrophilic binder.

21. A method according to claim 20, wherein said hydrophilic binder is polyvinyl alcohol.

20 22. A method according to claim 13, wherein said particulate polymer comprises low density polyethylene.

25 23. A method according to claim 22, wherein said particulate polymer comprises low density polyethylene particles having an average particle size of approximately 25 $\mu$ m.

24. A method according to claim 13, wherein the inks used to print the image on said receiving layer are selected from the groups consisting of aqueous inks, mineral oil inks and inks based on organic solvents.

5

10

15

20

25

30

## **ABSTRACT**

### **PRINTING PROCESS**

There is described a recording medium and related ink jet printing  
5 method which comprises the steps of:-

1) printing onto a receiving medium which comprises a substrate  
coated with at least one ink receiving layer comprising polymeric  
particles having film forming temperatures between 60° to 140°C and a  
binder, and

10 2) heating the printed image to form a stable image-protecting  
coating.

Preferably the printed image is heated by passing through a  
laminator. Alternatively the printed image is heated by passing through  
a laminator in conjunction with a second, inert releasing sheet which is  
15 held against the top surface of the print material. The second sheet  
may be used to produce a particular appearance to the final image  
such as high gloss or a security pattern. The receiving layers of the  
invention provide bright images after printing and fusing which show a  
high level of scratch and rub resistance even when wet.

20



## Declaration For Patent Application

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

## PRINTING PROCESS

the specification of which

(check one) ☒ [X] is attached hereto.

[ ] was filed on \_\_\_\_\_ as  
Application Serial No. \_\_\_\_\_  
and was amended on \_\_\_\_\_  
(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, Section 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)

Priority  
Claimed

<u>9927167.8</u>	<u>GREAT BRITAIN</u>	<u>18 NOVEMBER 1999</u>	[X]	[ ]
(Number)	(Country)	(Day/Month/Year Filed)	Yes	No

(Number)	(Country)	(Day/Month/Year Filed)	[ ] Yes	[ ] No
----------	-----------	------------------------	------------	-----------

I hereby claim the benefit under Title 35, United States Code, § 119(e) of any United States provisional application(s) listed below:

(Application Serial No.)

(Filing Date)

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose material information as defined Title 37, Code of Federal Regulations, § 1.56 which occurred between the filing date of the prior applications and the national or PCT international filing date of this application:

(Application Serial No.)

(Filing Date)

(Status) (patented,  
pending, abandoned)

(Application Serial No.)

(Filing Date)

(Status) (patented,  
pending, abandoned)

(Application Serial No.)

(Filing Date)

(Status) (patented,  
pending, abandoned)

As a named inventor, I hereby appoint the following attorney to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith: Dara L. Onofrio, 34,889.

Address all correspondence to Dara L. Onofrio, Esq., c/o THE LAW OFFICES OF DARA L. ONOFRIO, 233 Broadway Suite 270, New York, New York 10279-2799. Telephone No.: (212) 791-2950.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of first joint inventor Jeffrey Ronald KING  
Inventor's signature Jeffrey Ronald King Date OCT 11th 2000  
Residence 110 Portree Drive, Holmes Chapel, Cheshire CW4 7JB,  
England  
Citizenship: Great Britain  
Post Office Address same as above

Full name of second joint inventor, inventor Karen TAYLOR  
Inventor's signature Karen Taylor Date OCT 12th 2000  
Residence 139 Vernon Road, Poynton, Cheshire SK12 1YS, England  
Citizenship: Great Britain  
Post Office Address same as above

Full name of third joint inventor, Simon Richard John LEGGETT  
Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_  
Residence La Croix 378 CH-1633, Marsens, Switzerland  
Citizenship: Switzerland  
Post Office Address same as above

Full name of fourth joint inventor, Stefan SCHÜTTEL  
Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_  
Residence Oberes Neuqu 21 CH-3280 Murten Switzerland  
Citizenship: Switzerland  
Post Office Address same as above

Full name of fifth joint inventor, Roger Leslie BRETNALL  
Inventor's signature Roger Leslie Brettnall Date OCT. 11th 2000  
Residence 215 Hurdsfield Road, Macclesfield, Cheshire, SK 10 2PX,  
ENGLAND  
Citizenship: Great Britain  
Post Office Address same as above

[SWISS]

Declaration For Patent Application

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

PRINTING PROCESS

the specification of which

(check [X] is attached hereto.  
one)

[ ] was filed on \_\_\_\_\_ as  
Application Serial No. \_\_\_\_\_  
and was amended on \_\_\_\_\_  
(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, Section 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s)

Priority  
Claimed

<u>9927167.8</u>	<u>GREAT BRITAIN</u>	<u>18 NOVEMBER 1999</u>	[X] [ ]
(Number)	(Country)	(Day/Month/Year Filed)	Yes No

_____	_____	_____	[ ] [ ]
(Number)	(Country)	(Day/Month/Year Filed)	Yes No

00511 05421 000

I hereby claim the benefit under Title 35, United States Code, § 119(e) of any United States provisional application(s) listed below:

(Application Serial No.)

(Filing Date)

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose material information as defined Title 37, Code of Federal Regulations, § 1.56 which occurred between the filing date of the prior applications and the national or PCT international filing date of this application:

(Application Serial No.)

(Filing Date)

(Status) (patented,  
pending, abandoned)

(Application Serial No.)

(Filing Date)

(Status) (patented,  
pending, abandoned)

(Application Serial No.)

(Filing Date)

(Status) (patented,  
pending, abandoned)

As a named inventor, I hereby appoint the following attorney to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith: Dara L. Onofrio, 34,889.

Address all correspondence to Dara L. Onofrio, Esq., c/o THE LAW OFFICES OF DARA L. ONOFRIO, 233 Broadway - Suite 270, New York, New York 10279-2799. Telephone No.: (212) 791-2950.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

**Full name of first joint inventor** Jeffrey Ronald KING  
Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_  
Residence 110 Portree Drive, Holmes Chapel, Cheshire CW4 7JB, England  
Citizenship: Great Britain  
Post Office Address same as above

**Full name of second joint inventor, inventor** Karen TAYLOR  
Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_  
Residence 139 Vernon Road, Poynton, Cheshire SK12 1YS, England  
Citizenship: Great Britain  
Post Office Address same as above

**Full name of third joint inventor, Simon Richard John** LEGGETT  
Inventor's signature Simon Richard John Leggett Date 02.11.00  
Residence La Croix 378 CH-1633, Marsens, Switzerland  
Citizenship: Great Britain  
Post Office Address same as above

**Full name of fourth joint inventor, Stefan** SCHÜTTEL  
Inventor's signature Stefan Schüttel Date 26.10.00  
Residence Oberes Neugut 21 CH-3280 Murten Switzerland  
Citizenship: Switzerland  
Post Office Address same as above

**Full name of fifth joint inventor, Roger Leslie** BRETNALL  
Inventor's signature \_\_\_\_\_ Date \_\_\_\_\_  
Residence 215 Hurdsfield Road, Macclesfield, Cheshire, SK 10 2PX, ENGLAND  
Citizenship: Great Britain  
Post Office Address same as above